

COVALENCE[®] HTLP60

Product Information

A girth weld protection system for three-layer coated pipes.

Product description: Covalence[®] HTLP60 system is a wrap-around heat-shrinkable sleeve which replicates the structure and performance of mill-applied three-layer PE coatings. HTLP60 also has excellent compatibility and has been extensively used on many other mill-applied coatings (see below).

Construction: Three-layer system

- *First layer:* Liquid epoxy, solvent-free two-component.
- *Second layer:* High shear strength copolymer adhesive.
- *Third layer:* Radiation cross-linked, high density polyethylene with permanent Change Indicator (PCI).

During installation, the epoxy is applied to the prepared pipe surface and the heat-shrinkable sleeve is immediately wrapped around the joint over the wet epoxy. Heat is then applied to the sleeve which shrinks to form a tight fit around the joint. While curing, the epoxy forms strong mechanical and chemical bonds to the pipe surface & to the copolymer adhesive layer. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Features:

- Fully resistant to shear forces induced by soil and thermal movements.
- Sleeve applied over wet epoxy, allowing formation of strong mechanical & chemical bonds.
- Superior cathodic disbondment and hot water immersion resistance.
- Fully reconstructs the coating of three-layer coated pipes.
- Dimpled backing provides a "permanent change" indicator for application of heat.

Benefits:

- The HTLP is tough & lasts as long as a 3-layer, mill-applied coating.
- Allows fast application combined with high performance!
- Offers the optimum barrier protection against corrosion.
- HTLP systems allow the pipeline to have a virtually monolithic coating system.
- Ensures correct application heat & allows easy post-heat inspection. Reliable inspectability at any time.

Product selection guide

Max operating temperature	65°C (149°F).
Compatible line coatings	PE, FBE, Coal Tar, DFBE
Min. preheat temperature	70°C (158°F)
Recommended pipe preparation	Sa 2½
Soil stress restrictions	None
Performance	EN 12068 Class C50

Product properties

Backing		
Property	Test method	Typical value
Tensile strength at break	ASTM D 638	3300 psi (22.8 MPa)
Elongation at break	ASTM D 638	600%
Hardness, Shore D	ASTM D 2240	57
Shrink force	ASTM D 638, 150°C (302°F)	40 psi
Dielectric strength	ASTM D 149	900 V/mil (35 kV/mm)
Moisture absorption	ASTM D 570	0.04%
Adhesive		
Property	Test method	Typical value
Softening point	ASTM E 28	103°C (217°F)
Lap shear	ASTM D-1002 EN 12068 @10 mm (0.4")/min	350 psi @ 23°C (73°F) 11 psi @ 65°C (149°F) 0.22 N/mm ² @ 50°C (122°F)
Installed sleeve		
Property	Test method	Typical value
Peel to steel	EN 12068 @10 mm (0.4")/min	3.2 N/mm
Cathodic disbondment	ASTM G-42, 30 days, @ 65°C (149°F)	13 mm radius
Hot water immersion	ASTM D 870 120 days, @ 60°C (140°F)	No delamination, no blisters or water ingress
Soil stress creep resistance	TP-206 65°C (149°F)	0.009 mm (0.0004 in)
Low temperature flexibility	ASTM D 2671-C	-40°C (-40°F)
Impact resistance	EN 12068, Class C	> 15 J *
Indentation resistance	EN 12068, Class C @ 60°C (140°F)	Residual thickness > 0.6 mm *

* Construction /1.0-1.5 or thicker.

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.

Product thickness

Designation /...	/B	/1-1.5	/C	/2-1-8*
Backing as supplied	0.75 mm (0.030 in)	0.75 mm (0.030 in)	1.04 mm (0.041 in)	1.5 mm (0.060 in)
Backing fully free recovered	1.00 mm (0.039 in)	1.00 mm (0.039 in)	1.40 mm (0.055 in)	2.00 mm (0.079 in)
Adhesive as supplied	1.00 mm (0.039 in)	1.50 mm (0.060 in)	1.50 mm (0.060 in)	1.80 mm (0.071 in)

* Minimum order quantities apply

